

Deep Cycle AGM Batteries

C12-125XDA (12V / 125Ah)




Century AGM Deep Cycle Batteries are the ultimate in deep cycle battery performance, designed to provide longer life and dependable deep cycling capability in the harshest of operating conditions and environments.

The Century Deep Cycle AGM range utilises Absorbed Glass Mat (AGM) technology which absorbs the liquid electrolyte within highly porous glass fibre mat separators. This eliminates loose electrolyte whilst the sealed maintenance free design prevents acid leaks and the need for on-going maintenance. Extra strong grid designs, superior active paste material and robust internal components ensure lower self discharge, superior vibration resistance, longer cycle life and improved recharge capabilities.

Century Deep Cycle AGM batteries are ideal for use in applications where fast recharge, and superior deep cycle capabilities are required, such as recreational vehicles and accessories, dual battery systems, golf carts, electric wheel chairs, mobility scooters and marine systems.

Product Specification								
Cells	6	Weight	Approx. 35 kg					
Voltage	12	Max. Discharge Current	1250 A (5 sec)					
Capacity	125Ah@20hr-rate to 1.75V per cell @ 25°C	Internal Resistance	Approx. 4mΩ					
Operating Temperature Range	Discharge:-20°C~60°C	Terminal	M8 Insert					
	Charge: 0°C~50°C Storage: -20°C~60°C	Container Material	A.B.S. (UL94-HB)					
Normal Operating Temperature Range	25°C ± 5°C	Recommended Max. Charging - Current Limit	36A					
Float Charging Voltage	13.6 to 13.8 VDC/unit Average at 25°C	Equalisation & Cycle Service	14.6 to 14.8VDC/unit Average at 25°C					
Self Discharge	Century AGM batteries can be stored for more than 6 months at 25°C. Self-discharge rate less than 3% per month at 25°C. Please charge batteries before using.	Note: Warranty void if mounted under bonnet						

Unit: mm **Dimension:** 407 (L) x 177 (W) x 225 (H) x 225 (TH)





Discharge Curre	ent VS Discha	rge Voltage		Charge the batteries at least once a month every six months, if they are stored at 25°C			
Final Discharge Voltage V/Cell	1.75V	1.70V	1.60V	Charging Method			
Discharge Current	(A) ≤0.2C	0.2C< (A) <1.0C	(A) ≥1.0C	Constant Voltage	-0.2Cx2h+2.4~2.45V/Cellx24h,Max.Current 0.3CA		


Constant Current Discharge Characteristics: A (25°C) 15MIN F.V/Time 5MIN 10MIN 30MIN 1HR 2HR 3HR 4HR 5HR 8HR 10HR 20HR 9.60V 413.6 296.4 215.7 132.5 74.88 42.75 30.07 24.88 19.58 14.31 12.10 6.40 10.0V 402.6 282.0 211.2 130.3 74.53 42.43 29.95 24.77 19.47 14.19 11.98 6.28 207.9 10.2V 379.3 272.1 129.1 73.84 42.10 29.72 24.65 19.35 14.08 11.87 6.17 10.5V 340.6 251.0 198.0 125.9 73.15 41.78 29.61 24.42 19.12 13.96 11.75 6.05 307.4 23.85 11.63 10.8V 228.9 182.5 120.4 71.42 41.03 28.80 18.78 13.73 5.93 39.21 11.1V 267.6 204.6 163.7 112.8 67.85 27.53 22.69 17.97 13.15 11.29 5.58


onstant Power Discharge Characteristics: W (25°C)												
F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
9.60V	3939	2881	2121	1495	856.4	491.8	347.0	287.5	226.7	166.1	136.1	71.86
10.0V	3859	2751	2077	1476	852.2	489.8	346.3	286.8	225.3	165.4	134.7	71.17
10.2V	3643	2660	2049	1459	846.0	485.3	344.2	285.5	224.6	164.0	134.0	70.47
10.5V	3280	2458	1954	1426	837.7	480.8	342.1	283.4	222.6	162.6	132.6	69.77
10.8V	2951	2231	1795	1361	817.0	473.8	333.8	275.8	219.1	159.1	131.2	69.07
11.1V	2547	1982	1603	1275	774.1	451.9	317.3	262.7	208.1	153.5	127.0	66.28

All mentioned values are average values.











Battery Disposal This battery is 98% recyclable. Help create a cleaner planet, return your used battery to the original place of purchase or your nearest CenturyYuasa approved Battery Recycling Centre.